

# Arkimix PV7

ID: G1-PV7  
Version: 1  
Edition: 1



## General purpose PVA bonding agent

### Description

Arkimix PV7 is a ready to use multipurpose liquid PVA-based bonding agent and cement modifier.

### Key functions

Arkimix PV7 is used as an Integral bonding agent and for cement-based mixes as tile adhesives, plaster, repair mortars and screeds.

### Advantages

- Easy to use.
- Zero VOC. Environmentally friendly product.
- Improved mechanical properties of the cement mix.
- Good abrasion resistance.
- Improved adhesion to substrates.
- Reduced bleeding.

### Properties

<b>Type:</b>	Formulated copolymer emulsion
<b>Color:</b>	White
<b>Density:</b>	~1.01 Kg/L

### Application instructions

#### Dosage

Arkimix PV7 is added in a rate of 8 to 10 liters per 50 kg cement.

Note: The above dosage rates are a guide only. It is the contractor's / user's responsibility to ensure that all the materials to be used are compatible and further that they meet the design criteria and specification requirements.

#### Mixing

Preferably in a pan mixer but hand batching is permissible when the total weight of the mix is less than 25kg. Charge the mixer with the required quantity of sand and cement and pour in the required quantity of Arkimix PV7 and mix for 3 minutes only to avoid excessive air entrainment. Add water carefully until the required consistency is achieved.

#### Curing

Correct curing of Arkimix PV7 modified mixes is important. Moisture cure for at least 3 day and then allow to dry out slowly.

### Cleaning

Clean tools with water before hardening. Hardened material can only be removed mechanically.

### Watch-points

- Always use fresh cement and well-graded aggregate free of excessive fines.
- Keep mixing time to a minimum.
- Modified mixes are deceptive in their workability. Avoid using excess water.
- Protect from too rapid drying out prior to trowelling.

### Storage and shelf life

Arkimix PV7 has a maximum shelf life of 12 months when stored in good warehouse conditions away from direct sunlight in ambient temperature between 5°C and 35°C.

For ambient temperatures outside this range consult Arki for advice.

### Packaging

Arkimix PV7 is supplied in 4L and 20 L jenkins.

### Safety precautions

Arkimix PV7 is a non-flammable material.

Arkimix PV7 is not classified as hazardous material under current legislations.

Arkimix PV7 may cause irritation to the skin and eyes. Therefore, unnecessary contact with the product is to be avoided and suitable gloves and goggles must be worn.

Do not dispose into water or soil. Dispose the material according to local regulations.

Accidental contact of Arkimix PV7 to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, seek medical advice.

For further information, refer to the material safety data sheet.

### Technical support

Arki provides assistance to its customers and gives site support, consultations and technical advice on concrete repair, surface preparation and treatment, tile adhesive and tile grout selection and tile installation techniques.

# Arkimix PV7

---

## Additional Arki products

Arki produces high quality products intended for use in construction activity, among these products:

- Concrete Admixtures
- Concrete repair materials.
- Mould release agents and curing compounds.
- Waterproofing materials.
- Flooring systems.
- Tile adhesives and tile grouts
- Protective coatings.

## Product Quality

All Arki products are manufactured under a quality management system independently certified to conform to the requirements of the international standards.



P O Box 301100,  
Riyadh 11372, Saudi Arabia  
Tele: 920006343  
Fax: +966 1 4891700  
e-mail: info@arkichem.com

[www.arki.sa](http://www.arki.sa)

Users should always refer to the most recent issue of the product technical data-sheet for the product concerned, copies of which will be supplied on request.

Arki products are guaranteed against defective materials and manufacture and are sold subject to Arki standard terms and conditions of sales.

Because the storage, handling and application of these products are beyond our control, we can accept no liability for the results obtained.